

• Claims

1. An aromatic polyamide resin comprising an aromatic polyamide resin
having a melting point of at least 290°C, an inorganic filler, and an impact
5 modifier.
2. An aromatic polyamide resin composition of Claim 1 having a ratio of
the weight M of said inorganic filler to the weight T of said impact modifier of
 $2.0 \leq M/T \leq 6.5$.
3. An aromatic polyamide resin composition of Claims 1-2 wherein the
10 composition has a melt viscosity, measured with a capillary rheometer at a shear
rate of 1000/sec and a process temperature 20-30°C higher than the melting point
of said aromatic polyamide resin, of 350 Pa·sec or less.
4. An aromatic polyamide resin composition of Claims 1-3 wherein said
aromatic polyamide resin has a glass transition temperature of at least 60°C.
15